


TEX MMP

BIAXIALLY ORIENTED POLYPROPYLENE FILM

TEX MMP is a matte film, one side non sealable under 130°C and treated on the other side, coextruded BOPP film. Low gloss on the matte surface.



- 1 - TREATED SURFACE
- 2 - PP HOMOPOLYMER
- 3 - NON SEALABLE SURFACE UNDER 130°C

APPLICATION

Printing and laminations for general food packaging such as snacks, cookies/crackers, confections, cereal bars and other products that require a matte aspect on the package surface.

TYPICAL VALUES

Properties	Units	Typical Values	Method
		20TEX MMP	
THICKNESS	Gauge	79	ASTM D4321
YIELD	in ² /lb	40850	ASTM D4321
GLOSS EXTERNAL	u.b.	7	ASTM 2457
SURFACE TENSION	dynas/cm	>38	ASTM D2578
COF NT/NT	NA	0.25	ASTM D1894
SHRINKAGE MD	%	1.5	ASTM D1204
SHRINKAGE TD	%	0	ASTM D1204
TENSILE STRENGTH MD	Psi	21755	ASTM D882
TENSILE STRENGTH TD	Psi	39160	ASTM D882
ELONGATION MD	%	180	ASTM D882
ELONGATION TD	%	50	ASTM D882

Observations

1-The values described above may not be taken as the product specifications values. These values are based on the average or typical values generated at the time of production and should be considered as a reference only.

2- The films have their treatment at external side of the slit roll. Tecnoval is able to produce slit rolls with treatment at internal side under previously consulting to Commercial Area.

3- The technical information in this publication are based on our experience and are general. Users are suggested to conduct their own tests to determine suitability of these products for their own particular uses. The user is solely responsible for all determination regarding any use of the material or product and process in its interest.

4- The initial sealing temperature is above 130°C on the matte surface.

Abbreviations: MD - Machine Direction; DT - Transversal Direction; E - External Side; NT - Non treated side.

TECNOVAL LAMINADOS PLÁSTICOS LTDA

Street Leonardo Costa Gonçalves, n 1100 - Parque Monte Verde
City: Itamonte - MG - Zip code:37466-000
Phone: + 55 35 3363 9800

Review: 01/30/2019